

304/304L

STAINLESS STEEL

UNS S30400/UNS S30403



AK Steel Type 304 is a variation of the basic 18-8 grade, Type 302, with a higher chromium and lower carbon content. Lower carbon minimizes chromium carbide precipitation due to welding and its susceptibility to intergranular corrosion. In many instances, it can be used in the "as-welded" condition, while Type 302 must be annealed in order to retain adequate corrosion resistance.

Type 304L is an extra low-carbon variation of Type 304 with a 0.03% maximum carbon content that eliminates carbide precipitation due to welding. As a result, this alloy can be used in the "as-welded" condition, even in severe corrosive conditions. It often eliminates the necessity of annealing weldments except for applications specifying stress relief. It has slightly lower mechanical properties than Type 304.

Typical uses include architectural moldings and trim, kitchen equipment, welded components of chemical, textile, paper, pharmaceutical and chemical industry processing equipment.

AVAILABLE FORMS

AK Steel produces Type 304 Stainless Steel in thicknesses from 0.01" to 0.25" (0.025 to 6.35 mm) max. and widths up to 48" (1219 mm). For other thicknesses and widths, inquire.

COMPOSITION

	Type 304 %	Type 304L %
Carbon	0.08 max.	0.03 max.
Manganese	2.00 max.	2.00 max.
Phosphorus	0.045 max.	0.045 max.
Sulfur	0.030 max.	0.030 max.
Silicon	0.75 max.	0.75 max.
Chromium	18.00-20.00	18.0-20.0
Nickel	8.00-12.00	8.0-12.0
Nitrogen	0.10 max.	0.10 max.
Iron	Balance	Balance

SPECIFICATIONS

AK Steel Types 304 and 304L Stainless Steels are covered by the following specifications:

Type 304	Type 304L
AMS 5513	AMS 5511
ASTM A 240	ASTM A 240
ASTM A 666	ASTM A 666

MECHANICAL PROPERTIES

Typical Room Temperature Mechanical Properties

	UTS ksi (MPa)	0.2% YS ksi (MPa)	Elongation % in 2" (50.8 mm)	Hardness Rockwell
Type 304L	85 (586)	35 (241)	55	B80
Type 304	90 (621)	42 (290)	55	B82

PHYSICAL PROPERTIES

Density, 0.29 lbs/in³
8.03 g/cm³

Electrical Resistivity, microhm-in
(microhm-cm)
68°F (20°C) – 28.4 (72)
1200°F (659°C) – 45.8 (116)

Specific Heat, BTU/lb/°F (kJ/kg•K)
32 - 212°F (0 - 100°C) – 0.12 (0.50)

Thermal Conductivity, BTU/hr/ft²/ft/°F
(W/m•K)
at 212°F (100°C) – 9.4 (16.2)
at 932°F (500°C) – 12.4 (21.4)

Mean Coefficient of Thermal Expansion,
in/in/°F (µm/m•K)
32- 212°F (0 - 100°C) – 9.4 x 10⁻⁶(16.9)
32- 600°F (0 - 315°C) – 9.6 x 10⁻⁶(17.3)
32-1000°F (0 - 538°C) –10.2 x 10⁻⁶(18.4)
32-1200°F (0 - 649°C) –10.4 x 10⁻⁶(18.7)

Magnetic Permeability, H = 200
Oersteds, Annealed - 1.02 max.

Modulus of Elasticity, ksi (MPa)
28.0 x 10³ (193 x 10³) in tension
11.2 x 10³ (78 x 10³) in torsion

Melting Range, °F (°C) – 2550 - 2650
(1399 - 1454)

CORROSION RESISTANCE

These steels exhibit excellent resistance to a wide range of atmospheric, chemical, textile, petroleum and food industry exposures.

OXIDATION RESISTANCE

The maximum temperature to which Types 304 and 304L can be exposed continuously without appreciable scaling is about 1650°F (899°C). For intermittent exposure, the maximum exposure temperature is about 1500°F (816°C).

HEAT TREATMENTS

Type 304 is non-hardenable by heat treatment. Annealing: Heat to 1900 - 2050°F (1038 - 1121°C), then cool rapidly. Thin strip sections may be air cooled, but heavy sections should be water quenched to minimize exposure in the carbide precipitation region.

Stress Relief Annealing: Cold worked parts should be stress relieved at 750°F (399°C) for 1/2 to 2 hours.

FORMABILITY

Types 304 and 304L have very good drawability. Their combination of low yield strength and high elongation permits successful forming of complex shapes. However, these grades work harden rapidly. To relieve stresses produced in severe forming or spinning, parts should be full annealed or stress-relief annealed as soon as possible after forming.

WELDABILITY

The austenitic class of stainless steels is generally considered to be weldable by the common fusion and resistance

techniques. Special consideration is required to avoid weld "hot cracking" by assuring formation of ferrite in the weld deposit. Types 304 and 304L are generally considered to be the most common alloys of this stainless class. When a weld filler is needed, AWS E/ER 308, 308L or 347 are most often specified. Types 304 and 304L Stainless Steels are well known in reference literature and more information can be obtained in this way.

METRIC CONVERSION

Data in this publication are presented in U.S. customary units. Approximate metric equivalents may be obtained by performing the following calculations:

Length (inches to millimeters) –
Multiply by 25.4

Strength (ksi to megapascals or
meganewtons per square meter) –
Multiply by 6.8948

Temperature (Fahrenheit to Celsius) –
(°Fahrenheit - 32) Multiply by 0.5556

Density (pounds per cubic inch to
kilograms per cubic meter) –
Multiply by 27,670

The information and data in this product data sheet are accurate to the best of our knowledge and belief, but are intended for general information only. Applications suggested for the materials are described only to help readers make their own evaluations and decisions, and are neither guarantees nor to be construed as express or implied warranties of suitability for these or other applications.

Data referring to mechanical properties and chemical analyses are the result of tests performed on specimens obtained from specific locations with prescribed sampling procedures; any warranty thereof is limited to the values obtained at such locations and by such procedures. There is no warranty with respect to values of the materials at other locations.

AK Steel and the AK Steel logo are registered trademarks of AK Steel Corporation.

SPECIALTY AND STAINLESS STEEL FIELD SALES OFFICES**AK Steel Corporation**

703 Curtis Street
Middletown, OH 45043-0001
Customer Service 800-331-5050

Butler Works

P.O. Box 1609
Butler, PA 16003-1609
Customer Service 800-381-5663

Coshocton Works

17400 State Route 16
Coshocton, OH 43812
Customer Service 800-422-4422

AK Steel Sales Offices

Atlanta, GA-Southeast Region 770-514-0023
Baltimore, MD 410-612-1338
Charlotte, NC 704-662-0786
Chicago, IL-West Central Region 630-368-0001
Cincinnati, OH- Midwest Region 513-683-5300
Detroit, MI-North Central Region 248-641-7595
Grand Rapids, MI 616-949-5278
Nashville, TN-Southwest Region 615-771-3134
New England 401-658-3468
Pittsburgh, PA 412-635-9835
Tulsa, OK 918-298-2272
International Sales-Houston, TX ... 281-872-8741
Specialty Stainless and Electrical
Commercial-Butler, PA 800-381-5663

